

## **Amendments To The Claims**

This listing of claims will replace all prior versions, and listings, of claims in the application.

### **Listing of Claims:**

1. (Currently Amended) Method for reducing emissions of one or more gaseous substances, emitted from an exposed glue line of an assembly of at least two pieces of wooden materials which have been glued together, the one or more gaseous substances belonging to the group of aldehydes or isocyanates, comprising planing at least one of the sides having glue lines exposed, followed by treating ~~the~~ at least one planed side by application of a liquid treating composition containing one or more treating substances reactive to an aldehyde or an isocyanate.
2. (Cancelled)
3. (Cancelled)
4. (Cancelled)
5. (Previously Presented) Method according to claim 1, wherein one gaseous substance is formaldehyde.
6. (Previously Presented) Method according to claim 1, wherein one treating substance is urea or a urea derivative.
7. (Cancelled)
8. (Previously Presented) Method according to claim 1, wherein one treating substance is a reaction product of an alcohol and ammonia.
9. (Cancelled)
10. (Cancelled)

11. (Cancelled)

12. (Currently Amended) Method according to claim 1, wherein the treating composition comprises from about 1 to about 80 weight % of ~~the~~ one or more treating substances.

13. (Previously Presented) Method according to claim 1, wherein the treating composition comprises from about 0.02 to about 10 weight % of a polymer.

14. (Currently Amended) Method according to claim 1, wherein the treating composition comprises a ~~polyvinyl alcohol~~ polyvinyl alcohol dispersion.

15. (Currently Amended) Method for producing a laminated wooden product comprising the steps of:

(a) -applying an adhesive system onto one or more wooden lamellas,

(b) -assembling two or more wooden lamellas into an assembly,

(c) -pressing the assembly,

(d) -planing at least one of the sides of the assembly having glue lines exposed,  
and,

(e) -treating the one or more planed sides by application of a liquid treating composition containing one or more treating substances reactive to an aldehyde or an isocyanate emitted from ~~the~~ at least one planed side.

16. (Cancelled)

17. (Previously Presented) Method according to claim 15, wherein one gaseous substance is formaldehyde.

18. (Previously Presented) Method according to claim 15, wherein one treating substance is urea or a urea derivative.

19. (Cancelled)

20. (Previously Presented) Method according to claim 15, wherein one treating substance is a

reaction product of an alcohol and ammonia.

21. (Cancelled)

22. (Cancelled)

23. (Cancelled)

24. (Currently Amended) Method according to claim 15, wherein the treating composition comprises from about 1 to about 80 weight % of ~~the~~ one or more treating substances.

25. (Previously Presented) Method according to claim 15, wherein the treating composition comprises from about 0.02 to about 10 weight % of a polymer.

26. (Currently Amended) Method according to claim 15, wherein the treating composition comprises a ~~polyvinyl alcohol~~ polyvinyl alcohol dispersion.

27. (Original) Method according to claim 15, wherein the laminated wooden product is a laminated beam.

28. (Cancelled)

29. (Cancelled)

30. (Cancelled)

31. (Currently Amended) Method for reducing emissions of gaseous substances from a glued laminate, comprising the steps of:

(1) gluing together a plurality of lamellas with an adhesive substance capable of emitting at least one gaseous substance being an aldehyde or an isocyanate, thereby forming a laminated beam having exposed glue lines on at least one side thereof and from which said at least one gaseous substance can be emitted;

(2) planing said at least one side having exposed glue lines; and

(3) treating ~~the~~ at least one planed side by application of a liquid treating composition containing one or more treating substances reactive to an aldehyde or an isocyanate, thereby reducing or eliminating the emission of the aldehyde or the isocyanate.

32. (Previously Presented) Method according claim 1, wherein one treating substance contains an amino or amide group.

33. (Previously Presented) Method according claim 1, wherein one treating substance is a sulphite.

34. (Previously Presented) Method according claim 1, wherein one treating substance is an alcohol.

35. (Previously Presented) Method according claim 15, wherein one treating substance contains an amino or amide group.

36. (Previously Presented) Method according claim 15, wherein one treating substance is a sulphite.

37. (Previously Presented) Method according claim 15, wherein one treating substance is an alcohol.

38. (Currently Amended) Method according claim 1, further comprising ~~planing~~ planing at two sides having glue lines exposed to provide a first planed side and a second planed side facing opposite the first planed side, and applying said treating composition to both the first and second planed sides.

39. (Previously Presented) Method according claim 38, further comprising applying said treating composition simultaneously to both the first and second planed sides.

40. (Previously Presented) Method according claim 39, further comprising orienting the assembly so that the first planed side is facing upward and the second planed side is facing downward prior to applying said treating composition, and thereafter applying said treating

composition to the first planed side by spraying and to the second planed side by roller coating.

41. (Previously Presented) Method according claim 1, wherein said treating composition is applied in an amount of from about 0.1 to about 100 g/m<sup>2</sup>.

42. (Previously Presented) Method according claim 41, wherein said treating composition is applied in an amount of from about 1 to about 50 g/m<sup>2</sup>.

43. (Previously Presented) Method according claim 42, wherein said treating composition is applied in an amount of from about 5 to about 30 g/m<sup>2</sup>.

44. (Previously Presented) Method according claim 1, wherein said treating composition is applied from about 0.5 seconds to about 1 hour after planing.

45. (Previously Presented) Method according claim 44, wherein said treating composition is applied from about 0.5 seconds to about 1 minute after planing.

46. (Currently Amended) Method according claim 6, wherein said treating composition comprises about 10 to about 60 wt% urea and about 0.03 to about 2 wt% ~~polyvinyl alcohol~~ polyvinyl alcohol in the form of an aqueous ~~polyvinyl alcohol~~ polyvinyl alcohol dispersion.

47. (New) Method according to claim 1, further comprising a drying step after applying one or more treating compositions, wherein drying is by infra-red radiation, blowing with warm air, or microwave heating.

48. (New) Method according to claim 15, further comprising a drying step after applying one or more treating compositions, wherein drying is by infra-red radiation, blowing with warm air, or microwave heating.